

Elastomeric Impression Material

Type 0 (Putty / Hand-Mix) - Catalyst

Page 1 of 6

SECTION 1: Identification of the substance/mixture and of the company/undertaking

1.1. Product identifier

Elastomeric Impression Material – Type 0 (Putty / Hand-Mix) – Catalyst

1.2. Relevant identified uses of the substance or mixture and uses advised against

1.3. Details of the supplier of the safety data sheet

Company Name:	Shandong Huge Dental Material Corporation
Address:	No.68 shanhai Road, Donggang District
City, State, Zip Code:	Rizhao City, Shandong Province, 276800, P.R.China
Telephone:	86-633-2277268
email address:	marketing@hugedental.com
Website:	www.hugedental.com

SECTION 2: Hazards identification

2.1. Classification of the substance or mixture

Health hazards

Inhalation: Quartz : When encapsulated in polymer, it is not expected to pose a health hazard when processed under normal conditions of use.

Eye contact: No specific symptoms noted.

Skin contact: No specific symptoms noted.

Ingestion: No specific symptoms noted.

Other Health Effects: No other information noted.

Environmental hazards: Not regarded as dangerous for the environment.

2.2. Label elements

No risks worthy of mention.

2.3. Other hazards

No risks worthy of mention. Please observe the information on the safety data sheet at all times.

SECTION 3: Composition/information on ingredients

Chemical characterization

General information: Mixture of vinyl polysiloxane, fillers, additives. Hazardous components

Chemical name	Concentration	CAS-No.	EC No.	REACH Registration No.	Notes
Cristobalite	<=55%	14464-46-1	238-455-4		#
White mineral oil (petroleum)	<=8%	8042-47-5			#
Kieselguhr, soda ash flux-calcined	<=3%	68855-54-9			

Classification:

Chemical name	Classification		Notes
Cristobalite	DPD:	Xn; R48/20	
White mineral oil (petroleum)	DPD:	Xn; R65	
	CLP:	Asp. Tox. 1;H304	
Kieselguhr, soda ash flux-calcined	DPD:	Xn; R48/20	

DPD: Directive 67/548/EEC.

CLP: Regulation No. 1272/2008.:



Elastomeric Impression Material

Type 0 (Putty / Hand-Mix) – Catalyst

Page 2 of 6

SECTION 4: First aid measures

4.1. Description of first aid measures

After inhalation

Not applicable

After contact with skin

Remove contaminated clothing and shoes. Wash with soap and water.

After contact with eyes

In the event of contact with the eyes, rinse thoroughly with clean water. Continue to rinse for at least 15 minutes.

After ingestion

Do not induce vomiting. Rinse mouth thoroughly.

Most important symptoms and effects, both acute and delayed

None known.

Indication of any immediate medical attention and special treatment needed

Hazards: No specific recommendations.

Treatment: No specific recommendations.

SECTION 5: Firefighting measures

5.1. Extinguishing media

Suitable extinguishing media

Extinguish with foam, carbon dioxide or dry powder. Water spray.

Extinguishing media which must not be used for safety reasons None known

Advice for firefighters Special Fire Fighting Procedures

Water spray should be used to cool containers.

Special protective equipment for fire-fighters

Self-contained breathing apparatus and full protective clothing must be worn in case of fire.

SECTION 6: Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures

Use personal protective equipment. See Section 8 of the MSDS for Personal Protective Equipment. Environmental Precautions.

6.2. Environmental precautions

Collect spillage. Do not discharge into drains, water courses or onto the ground.

6.3. Methods and material for containment and cleaning up

Containers with collected spillage must be properly labelled with correct contents and hazard symbol. Container must be kept tightly closed. Absorb with sand or other inert absorbent. To clean the floor and all objects contaminated by this material, use an appropriate solvent. Flush area with plenty of water. Incinerate in suitable combustion chamber.

SECTION 7: Handling and storage

7.1. Precautions for safe handling

No specific precautions.

7.2. Conditions for safe storage. including any incompatibilities

No special storage precautions noted. Material is stable under normal conditions. Avoid contact with oxidizing agents. Suitable containers:polyethylene. Plastic lined steel drum.



Elastomeric Impression Material

Type 0 (Putty / Hand-Mix)[–] Catalyst

Page 3 of 6

SECTION 8: Exposure controls/personal protection

8.1. Control parameters

Occupational exposure limits

Quartz : When encapsulated in polymer, it is not expected to pose a health hazard when processed under normal conditions of use.

Chemical name	Туре	Exposure Limit values	Source
White mineral oil (petroleum) -	TWA	5 mg/m3	Italy. OELs (2009)
Inhalable fraction.			

8.2. Exposure controls

General information:

No specific precautions.

Eye/face protection:

Safety Glasses

Skin protection:

Hand protection: Use protective gloves made of: Nitrile. Polyvinyl chloride (PVC). Rubber or plastic.

Other:

No skin protection is ordinarily required under normal conditions of use. In accordance with good industrial hygiene practices, precautions should be taken to avoid skin contact.

Respiratory Protection:

No specific precautions.

Hygiene measures:

Provide eyewash station and safety shower.

Environmental Controls:

No data available.

SECTION 9: Physical and chemical properties

9.1. Information on basic physical and chemical properties

Appearance

Form:No data available.Color:WhiteOdor:OdorlessOdor Threshold:No data available.pH:Not applicableMelting Point:No data available.Boiling Point:No data available.Boiling Point:No data available.Flash Point:> 200 °C (Closed cup according to method ASTM D-56.)Evaporation Rate:No data available.Flammability (solid, gas):No data available.Flammability Limit - Upper (%):No data available.Flammability Limit - Lower (%):No data available.Vapor pressure:< 0,1 hPa (20 °C)Vapor density (air=1):No data available.Relative density:1,55 (20 °C) ApproximateSolubility (ies)Solubility in Water:Practically InsolubleSolubility (other):Diethylether.: Miscible (in all proportions).Common organic solvents.:Miscible (in all proportions).	-	Physical State:	Paste
Color:WhiteOdor:OdorlessOdor Threshold:No data available.pH:Not applicableMelting Point:No data available.Boiling Point:No data available.Flash Point:> 200 °C (Closed cup according to method ASTM D-56.)Evaporation Rate:No data available.Flammability (solid, gas):No data available.Flammability (solid, gas):No data available.Flammability Limit - Upper (%):No data available.Flammability Limit - Lower (%):No data available.Vapor pressure:< 0,1 hPa (20 °C)		•	
Odor:OdorlessOdor Threshold:No data available.pH:Not applicableMelting Point:No data available.Boiling Point:No data available.Flash Point:> 200 °C (Closed cup according to method ASTM D-56.)Evaporation Rate:No data available.Flammability (solid, gas):No data available.Flammability (solid, gas):No data available.Flammability Limit - Upper (%):No data available.Flammability Limit - Lower (%):No data available.Vapor pressure:< 0,1 hPa (20 °C)			
Odor Threshold: No data available. pH: Not applicable Melting Point: No data available. Boiling Point: No data available. Boiling Point: No data available. Flash Point: > 200 °C (Closed cup according to method ASTM D-56.) Evaporation Rate: No data available. Flammability (solid, gas): No data available. Flammability (solid, gas): No data available. Flammability Limit - Upper (%): No data available. Flammability Limit - Lower (%): No data available. Vapor pressure: < 0,1 hPa (20 °C)			
pH:Not applicableMelting Point:No data available.Boiling Point:No data available.Flash Point:> 200 °C (Closed cup according to method ASTM D-56.)Evaporation Rate:No data available.Flammability (solid, gas):No data available.Flammability Limit - Upper (%):No data available.Flammability Limit - Lower (%):No data available.Vapor pressure:< 0,1 hPa (20 °C)			
Melting Point:No data available.Boiling Point:No data available.Flash Point:> 200 °C (Closed cup according to method ASTM D-56.)Evaporation Rate:No data available.Flammability (solid, gas):No data available.Flammability Limit - Upper (%)-:No data available.Flammability Limit - Upper (%)-:No data available.Flammability Limit - Lower (%)-:No data available.Vapor pressure:< 0,1 hPa (20 °C)			
Boiling Point:No data available.Flash Point:> 200 °C (Closed cup according to method ASTM D-56.)Evaporation Rate:No data available.Flammability (solid, gas):No data available.Flammability Limit - Upper (%)-:No data available.Flammability Limit - Lower (%)-:No data available.Flammability Limit - Lower (%)-:No data available.Vapor pressure:< 0,1 hPa (20 °C)		pH:	Not applicable
Flash Point:> 200 °C (Closed cup according to method ASTM D-56.)Evaporation Rate:No data available.Flammability (solid, gas):No data available.Flammability Limit - Upper (%):No data available.Flammability Limit - Lower (%):No data available.Vapor pressure:< 0,1 hPa (20 °C)		Melting Point:	No data available.
Evaporation Rate: No data available. Flammability (solid, gas): No data available. Flammability Limit - Upper (%): No data available. Flammability Limit - Lower (%): No data available. Flammability Limit - Lower (%): No data available. Vapor pressure: < 0,1 hPa (20 °C)		Boiling Point:	No data available.
Flammability (solid, gas): No data available. Flammability Limit - Upper (%)-: No data available. Flammability Limit - Lower (%)-: No data available. Flammability Limit - Lower (%)-: No data available. Vapor pressure: < 0,1 hPa (20 °C)		Flash Point:	> 200 °C (Closed cup according to method ASTM D-56.)
Flammability Limit - Upper (%)-: No data available. Flammability Limit - Lower (%)-: No data available. Vapor pressure: < 0,1 hPa (20 °C)		Evaporation Rate:	No data available.
Flammability Limit - Lower (%)-: No data available. Vapor pressure: < 0,1 hPa (20 °C)		Flammability (solid, gas	s): No data available.
Vapor pressure:< 0,1 hPa (20 °C)		Flammability Limit - Up	per (%)–: No data available.
Vapor density (air=1):No data available.Relative density:1,55 (20 °C) ApproximateSolubility(ies)Practically InsolubleSolubility in Water:Practically InsolubleSolubility (other):Diethylether.: Miscible (in all proportions).Common organic solvents.:Miscible (in all proportions).		Flammability Limit - Lov	ver (%)–: No data available.
Relative density:1,55 (20 °C) ApproximateSolubility(ies)Practically InsolubleSolubility in Water:Practically InsolubleSolubility (other):Diethylether.: Miscible (in all proportions).Common organic solvents.:Miscible (in all proportions).		Vapor pressure:	< 0,1 hPa (20 °C)
Solubility(ies)Practically InsolubleSolubility in Water:Practically InsolubleSolubility (other):Diethylether.: Miscible (in all proportions).Common organic solvents.:Miscible (in all proportions).		Vapor density (air=1):	No data available.
Solubility in Water:Practically InsolubleSolubility (other):Diethylether.: Miscible (in all proportions).Common organic solvents.:Miscible (in all proportions).		Relative density:	1,55 (20 °C) Approximate
Solubility (other):Diethylether.: Miscible (in all proportions).Common organic solvents.:Miscible (in all proportions).		Solubility(ies)	
Common organic solvents.: Miscible (in all proportions).		Solubility in Water:	Practically Insoluble
		Solubility (other):	Diethylether.: Miscible (in all proportions).
Aromatic hydrocarbons.: Miscible (in all proportions).		Common organic solve	nts.: Miscible (in all proportions).
		Aromatic hydrocarbons	.: Miscible (in all proportions).
Aliphatic hydrocarbons.: Miscible (in all proportions).		Aliphatic hydrocarbons	: Miscible (in all proportions).
Acetone.: Very slightly soluble.		Acetone .:	Very slightly soluble.



	omeric Impression Material Type 0 (Putty / Hand-Mix) – Catalyst	Page 4 of 6
Ethanol.:	Very slightly soluble.	
Partition coefficient (n-octanol/	vater): No data available.	
Autoignition Temperature:	> 400 °C	
Decomposition Temperature:	> 200 °C	
Viscosity: No data available.		
Explosive properties:	No data available.	
Oxidizing properties:	According to the data on the components Not considered as	

oxidizing. (evaluation by structure-activity relationship)

SECTION 10: Stability and reactivity

10.1.Reactivity

Not relevant.

10.2.Chemical stability

Stable

10.3.Possibility of hazardous reactions

No data available.

10.4.Conditions to avoid

No other information noted.

10.5.Incompatible materials

Strong oxidizing agents.

10.6.Hazardous decomposition products

Thermal decomposition or combustion may liberate carbon oxides and other toxic gases or vapors. Amorphous silica.

SECTION 11: Toxicological information

11.1. Information on likely routes of exposure

Inhalation:No effects expected (assessment based on ingredients).Ingestion:No effects expected (assessment based on ingredients).Skin contact:No effects expected (assessment based on ingredients).Eye contact:No effects expected (assessment based on ingredients).

11.2.Information on toxicological effects

Acute toxicity

Oral:			
Product:	No effects expected (assessment based on ingredients).		
Dermal:			
Product:	No effects expected (assessment based on ingredients).		
Specified substance(s):			
Cristobalite	No data available.		
White mineral oil (pe	troleum) No data available.		
Kieselguhr, soda asł	n fluxcalcined No data available.		
Irritation and corrosivity			
Product:	No effects expected (assessment based on ingredients).		
Repeated dose toxic	ity:		
Product:	No effects expected (assessment based on ingredients).		
Skin corrosion/irritati	Skin corrosion/irritation:		
Product:	No effects expected (assessment based on ingredients).		
irritation:			
Product:	No effects expected (assessment based on ingredients).		
Respiratory or skin			
sensitization:			
Product:	No effects expected (assessment based on ingredients).		
Germ cell mutagenicity	1 (3)		
In vitro:			
Product:	No effects expected (assessment based on ingredients).		
In vivo:			
Product:	No effects expected (assessment based on ingredients).		
1100000			



Elastomeric Impression Material

Type 0 (Putty / Hand-Mix) – Catalyst

Page 5 of 6

Carcinogenicity: Product: No effects expected (assessment based on ingredients). Reproductive toxicity: Product: No effects expected (assessment based on ingredients). Specific target organ toxicity - single exposure: Product: No effects expected (assessment based on ingredients). Specific target organ toxicity - repeated exposure: Product: No effects expected (assessment based on ingredients). Aspiration hazard: Product: No effects expected (assessment based on ingredients). Other adverse effects: None known.

SECTION 12: Ecological information

12.1. Toxicity

Acute toxicity: Fish: Product: No effects expected (assessment based on ingredients). Aquatic invertebrates: Product: No effects expected (assessment based on ingredients). Chronic Toxicity: Fish: Product: No effects expected (assessment based on ingredients). Aquatic invertebrates: Product: No effects expected (assessment based on ingredients). Toxicity to Aquatic Plants: Product: No effects expected (assessment based on ingredients).

12.2. Persistence and degradability

Biodegradation:

Product: Not applicable

BOD/COD ratio:

Product: No data available.

Specified substance(s):

Cristobalite: No data available.

White mineral oil (petroleum): No data available.

Kieselguhr, soda ash fluxcalcined: No data available.

Bioaccumulation potential: No date available

Further information

If the material causes hormonal effects or prevents them is unknown to us.

SECTION 13: Disposal considerations

13.1. Waste treatment methods

General information

The user's attention is drawn to the possible existence of local regulations regarding disposal.

Disposal Methods

Dispose of waste at an appropriate treatment and disposal facility in accordance with applicable laws and regulations, and product characteristics at time of disposal. Incinerate in suitable combustion chamber.Contaminated packages should be as empty as possible. Dispose of waste at an appropriate treatment and disposal facility in accordance with applicable laws and regulations, and product characteristics at time of disposal. Recycle following cleaning or dispose of at an authorised site.



SHANDONG HUGE DENTAL MATERIAL CORPORATION www.hugedental.com



Elastomeric Impression Material Type 0 (Putty / Hand-Mix) – Catalyst

Page 6 of 6

SECTION 14: Transport information

None

SECTION 15: Regulatory information

15.1. Safety, health and environmental regulations/legislation specific for the substance or mixture

National regulatory information

Chemical safetyassessment:No data available.

SECTION 16: Other information

No further technical information

The present data sheet contains technical-scientific information processed at best of our knowledge. We recommend verifying national and regional regulations applicable to the specific utilize field as well as regulations relative hygienic and safety on work and environment worship.

All information contained in the present data sheet is correct and processed in good faith. However they do not involve any obligation, guarantee and patent concession.

The characteristics mentioned in the following document do not constitute contractual specifications.