Enamel Coating Resin

Page 1 of 4

SECTION 1: Identification of the substance/mixture and of the company/undertaking

1.1. Product identifier

Enamel Coating Resin

1.2. Relevant identified uses of the substance or mixture and uses advised against

Enamel Coating Resin is a visible light curing sealing material for coating on enamel:

- Areas of pit and fissure sealing
- Filling and protecting enamel surface minor defects or suspicious early carious
- Infiltrating into enamel surface and covering underneath enamel structure

1.3. Details of the supplier of the safety data sheet

Company Name: Rizhao HuGe Biomaterials Co., Ltd.

Address: 2 North Zhaoyang Road, Donggang District
City, State, Zip Code: Rizhao City, Shandong Province, China, 276800
Telephone: Tel: 86-633-2277268, Fax: 86-633-2277298

Email address: marketing@hugedental.com
Website: www.hugedental.com

SECTION 2: Hazards identification

2.1 Health Hazard

Emergency Overview

Specific Physical Form: Paste

Odor, Color, Grade: Methacrylate resin odor, tooth-colored paste of various shades

General Physical Form: Solid

Immediate health, physical, and environmental hazards: May cause allergic skin reaction. This document has been prepared in accordance with the U.S. OSHA Hazard Communication Standard, which requires the inclusion of all known hazards of the product or ingredients regardless of the potential risk. The risks of the hazards communicated in

this document may vary depending on the potential for exposure.

Risk identification: None known

Special risks for human

Beings and environment: None known

Classification: Not hazardous. Those people known to be allergic to dental methacrylate resins should avoid the use

of this product.

SECTION 3: Composition/information on ingredients

Element	CAS#	Exposure Limit OSHA PEL	
UDMA	72869-86-4	NE	NE
TEGDMA	109-16-0	NE	NE
ТМРТМА	3290-92-4	NE	NE
Photo-initiators	mixture	NE	NE
Silica (amorphous)	69012-64-2	NE	2R

Chemical characteristics: paste form of light curable of dental methacrylate resins comprising of UDMA, TEGDMA, TMPTMA; amorphous silica; with additives such as photo curing initiators, stabilizers.

Enamel Coating Resin

Page 2 of 4

SECTION 4: First aid measures

4.1 General Information:

After skin contact: Wash with plenty of soap and water.

After eye contact: Rinse with plenty of water and contact an ophthalmologist.

After swallowing: Seek medical advice immediately.

SECTION 5: Firefighting measures

Extinguishing media: CO₂, water, foam, dry chemical Protective equipment: Common gear for small commodities.

SECTION 6: Accidental release measures

Personal precautions: Avoid skin contact, wear protective equipment.

Environmental precautions: Absorb with inert material. Collect in closed containers and dispose of as recommended.

Methods for cleaning up: Dispose according to Federal, State and local regulations.

Additional information: Unknown.

SECTION 7: Handling and storage

7.1. Precautions for safe handling

Avoid contact with skin and eyes. Use at room temperature. Practice good hygienic measures.

7.2. Conditions for safe storage, including any incompatibilities

Keep container closed; store between 2° C ~25 $^{\circ}$ C. Refrigeration when not in use is recommended; Store away from direct sunlight, oxidizing and/or reducing agents or other incompatible matters.

SECTION 8: Exposure controls/personal protection

Personal protective equipment: Protective gloves, goggles are recommended.

General Measure of protection: Normal hygienic measures.

Respiration: Not necessary **Hands:** Protective gloves.

Eyes: OSHA approved goggles or glasses.

SECTION 9: Physical and chemical properties

9.1 Appearance:

Form: Paste
Color: Shaded
Odor: Ester-like

9.2 Information on change in the physical state

Melting point/melting range:

Boiling point/boiling range:

Unknown
Unknown
Unknown
Auto-ignition temperature:

Unknown
Unknown
Unknown
Unknown
Unknown
Unlikely

Density (combined): Approximately2.0 gm/cm³

Vapor pressure: Unknown

Enamel Coating Resin

Page 3 of 4

pH (combined): Unknown
Solubility in/miscibility with water: Slightly
Contents of solvents: None

Content of Solids (combined): $\leq 30 \%$ by weight

SECTION 10: Stability and reactivity

Incompatibility with other substances: Stable. Avoid exposure the material to peroxide, amine and excessive heat.

Hazardous decomposition products: Unknown.

SECTION 11: Toxicological information

This product has been found complying with ISO 10993 for complete biocompatibility assessments based on the criteria of the test protocols.

SECTION 12: Ecological information

General information: Unknown **Classification of water endangerment:** Not determined

SECTION 13: Disposal considerations

Dispose in accordance with Federal, State and local regulations.

SECTION 14: Transport information

UN number: None class: None packaging group: None ocean harmful substances: None

other relevant information: Not classified as dangerous goods. Protect it against humidity . Store it away from

food stuffs, acids, and bases.

SECTION 15: Regulatory information

311/312 Hazard Categories: Fire Hazard - No; Pressure Hazard - No; Reactivity Hazard - No; Immediate Hazard -

Yes; Delayed Hazard - No

Classification according to EEC guidelines: Unknown

National Prescriptions: Unknown

SECTION 16: Other information

No further technical information

The present data sheet contains technical-scientific information processed at best of our knowledge. We recommend verifying national and regional regulations applicable to the specific utilize field as well as regulations relative hygienic and safety on work and environment worship.

Enamel Coating Resin

Page 4 of 4

All information contained in the present data sheet is correct and processed in good faith. However they do not involve any obligation, guarantee and patent concession.

The characteristics mentioned in the following document do not constitute contractual specifications.

The data for the hazardous ingredients were taken respectively from the last version of the sub-contractor's safety data sheet.